

GT-PET-L-120 SPECIFICATION SHEET

Applications

Specialty sealant heat sealable lidding film designed for a tight to lock seal to APET trays.

Typical Properties

Properties	Value	Test method
Thickness (Gauge)	30.5(mic) 1.2(mil)	
Yield (in ² /lbs)	16,500	
Tensile strength (lb/in ²)	36,000 (MD) 39,000 (TD)	ASTM D 882
Elongation @ break (%)	150 (MD) 130 (TD)	ASTM D 882
OTR (24hrs @ 23°C/Dry)	4.0 (cc/100 in ² /24hr)	ASTM D 3985
WVTR (24hrs @ 38°C / 100% RH)	1.5 (g/100 in ² /24 hr)	ASTM F 1249

Teinnovations LLC and its affiliates make no representation or warranty regarding the information contained herein. The information above should be used as typical values of the applicable product and Teinnovations assumes no liability in connection with the use of such information or findings.

