

LTX-244 SPECIFICATION SHEET

Applications

Multi-purpose film that seals and peels cleanly from, itself or substrates such as APET, CPET, PETG, PP, HDPE, PS, HIPS, PVC, and PET or PE coated trays and containers.

Typical Properties

Properties	Value	Test method
Thickness (Gauge)	62	
Tensile strength (kg/15 mm)	4.0 (MD)	ASTM D 882
	3.0 (TD)	
Elongation @ break (%)	40 (MD)	ASTM D 882
	50 (TD)	
OTR (24hrs @ 23°C/Dry)	140.0 (cc/m ²)	ASTM D 3985
	9.03 (cc/100 in ²)	
WVTR (24hrs @ 38°C / 100% RH)	13.0 (g/m ²)	ASTM F 1249
	0.84 (g/100 in ²)	

Recommended sealing range: 140 – 180 C / 284 – 356 F

Teinnovations LLC and its affiliates make no representation or warranty regarding the information contained herein. The information above should be used as typical values of the applicable product and Teinnovations assumes no liability in connection with the use of such information or findings.

