

LTX-263

Specification Sheet



Issue Date: 9/13/2024

Applications

Multi-purpose lidding film that seals and peels cleanly from, itself or substrates such as APET, CPET, RPET, PP, HDPE, PS, HIPS, PVC, PLA, Fiberboard and Paperboard.

Recommended sealing range: 130 – 210 C / 266 – 410 F

Properties	Value	Test Method
Thickness	67 (micron)	FTM
	2.63 (mil)	
Tensile Strength	> 4.0 (MD)	ASTM D882
	> 3.0 (TD)	
Elongation	> 40 (MD)	ASTM D882
	> 50 (TD)	
OTR (24hrs @ 25°C/Dry)	< 140.0 (cc/m ²)	ASTM D3985
	< 9.03 (cc/100 in ²)	
WVTR (24hrs @ 23°C / 50% RH)	< 13.0 (g/m ²)	ASTM F1249
	< 0.84 (g/100 in ²)	

Teinnovations LLC and its affiliates make no representation or warranty regarding the information contained herein. The information above should be used as typical values of the applicable product and Teinnovations assumes no liability in connection with the use of such information or findings.



www.teinnovations.com



700 N. Commerce St.
Aurora, IL 60504



630-393-0012